



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	379 MPa
Ultimate tensile strength	664 MPa
Elongation	8 %
Elastic modulus	200 GPa
Vickers hardness	245 HV 10
Density	8,3 g/cm ³
Melting range	1290 - 1350 °C
Preheating temperature	850 - 950 °C
Casting temperature	1450 - 1500 °C
CTE (25 - 600 °C)	14,4 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	4

QUANTITY	REF
1000 g	139000



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	340 - 355 MPa
Ultimate tensile strength	490 - 510 MPa
Elongation	5 %
Elastic modulus	200 GPa
Vickers hardness	200 HV 10
Density	8,2 - 8,3 g/cm ³
Melting range	1310 - 1410 °C
Preheating temperature	850 - 950 °C
Casting temperature	1510 - 1560 °C
CTE (25 - 600 °C)	14,0 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	3

QUANTITY	REF
1000 g	131000

MOGUCERA N

NiCr bonding alloy for conventional, high-fusing (low expansion) ceramics.

- › Free of beryllium, cadmium and lead
- › Type 4 pursuant to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and extremely corrosion resistant

Composition (mass percentage):

Ni: 62 % / Cr: 24 % / Mo: 11 % / Si: 1,6 % / Mn: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ Wide range of indications
- ★ Best melting and casting properties
- ★ System-free working due to very good alloy properties
- ★ Pleasant polishing properties and easy finishing due to low hardness of 245 HV10
- ★ Flexibility in ceramic selection and safe veneering
- ★ Excellent metal-ceramic bonding, even without bonder
- ★ An oxidation firing can be omitted
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking

STARBOND NI

NiCr bonding alloy for conventional, high-fusing (low expansion) ceramics.

- › Free of beryllium, cadmium and lead
- › Type 3 pursuant to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and extremely corrosion resistant

Composition (mass percentage):

Ni: 60,7 % / Cr: 24 % / Mo: 11 % / Fe: 1,5 % / Si: 1,8 % / C: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ System-free working due to very good alloy properties
- ★ Pleasant polishing properties and easy finishing due to low hardness of 200 HV10
- ★ Flexibility in ceramic selection and safe veneering
- ★ Excellent metal-ceramic bonding, even without bonder
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking
- ★ An oxidation firing can be omitted

**PRESERVING
TRADITIONAL
DENTAL ALLOYS**



**HIGH-QUALITY
DENTAL ALLOYS –
MADE IN GERMANY**

Our modern and highly efficient production facility in Germany enables the manufacturing of premium dental alloys for conventional processing.

All our alloys are certified medical devices that meet the highest quality and safety standards, ensuring reliable and safe application.

In addition to our proven standard range, we offer the flexibility to produce **customized specifications** according to the highest safety and quality requirements directly at our facility. Furthermore, we provide **contract manufacturing according to your specific guidelines**.

Join the Scheftner New Generation and benefit from our expertise and innovative strength. Contact us now for more information!

CONTACT OUR TEAM FOR CUSTOM SPECIFICATIONS OR CONTRACT MANUFACTURING!



Scheftner GmbH
Dekan-Laist-Straße 52 · 55129 Mainz / Germany

Tel.: +49 (0) 61 31-94 71 40
Fax: +49 (0) 61 31-94 71 440

E-Mail: service@scheftner.dental
online: www.scheftner.dental



Starbond CoS

**PRESERVING
TRADITIONAL
DENTAL ALLOYS**

NON-PRECIOUS METAL ALLOYS (NPM)

Our non-precious metal alloys are characterized by excellent oral resistance and outstanding mechanical properties. Different compositions guarantee all restoration indications. Whether veneering with ceramic and acrylics, model casting and superstructures, our alloys produce highly aesthetic and natural results in excellent quality.



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	650 MPa
Ultimate tensile strength	910 MPa
Elongation	8 %
Elastic modulus	200 GPa
Vickers hardness	280-295 HV 10
Density	8,8 g/cm ³
Melting range	1305 - 1400 °C
Preheating temperature	850 - 950 °C
Casting temperature	1500 - 1550 °C
CTE (25 - 600 °C)	14,0 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	5

QUANTITY	REF
1000 g	133000
250 g	133250



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	610 MPa
Ultimate tensile strength	830 MPa
Elongation	10 %
Elastic modulus	190 GPa
Vickers hardness	285 HV 10
Density	8,7 g/cm ³
Melting range	1310 - 1410 °C
Preheating temperature	850 - 950 °C
Casting temperature	1480 - 1530 °C
CTE (25 - 600 °C)	14,4 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	4

QUANTITY	REF
1000 g	140000
250 g	140250

★ STARBOND COS

CoCrWMo bonding alloy for conventional, high-fusing (low expansion) ceramics.

- › Free of nickel, lead, beryllium and cadmium
- › Type 5 according to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and corrosion-resistant

Composition (mass percentage):

Co: 59 % / Cr: 25 % / W: 9,5 % / Mo: 3,5 % / Si: 1 % / C, Fe, Mn, N: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ Wide range of indications
- ★ System-free working due to very good alloy properties
- ★ Pleasant polishing properties and easy finishing due to low hardness of 280 HV10
- ★ A CTE of 14.0 enables flexibility in ceramic selection and safe veneering
- ★ No cooling phase required, depending on the ceramics
- ★ Excellent metal-ceramic bonding, even without bonder
- ★ An oxidation firing can be omitted
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking

★ STARBOND EASY

CoCrW bonding alloy for conventional, high-fusing (low expansion) ceramics.

- › Free of nickel, lead, beryllium and cadmium
- › Type 4 according to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and corrosion-resistant

Composition (mass percentage):

Co: 61 % / Cr: 27,5 % / W: 8,5 % / Si: 1,6 % / C, Mn, Fe: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ System-free working due to very good alloy properties
- ★ Pleasant polishing properties and easy finishing due to low hardness of 285 HV10
- ★ A CTE of 14.4 enables flexibility in ceramic selection and safe veneering
- ★ No cooling phase required, depending on the ceramics
- ★ Excellent metal-ceramic bonding, even without bonder
- ★ An oxidation firing can be omitted
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking

CONTACT OUR TEAM FOR CUSTOM SPECIFICATIONS OR CONTRACT MANUFACTURING!

★ MOGUCERA C

CoCrMo bonding alloy for conventional, high-fusing (low expansion) ceramics.

- › Free of nickel, lead, beryllium and cadmium
- › Type 5 according to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and corrosion-resistant

Composition (mass percentage):

Co: 65 % / Cr: 28 % / Mo: 5 % / Mn: 1 % / C, Si: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ Very good alloy properties enable system-free operation
- ★ Very easy to polish and easy working characteristics due to a low hardness of 300 HV10
- ★ A CTE of 14.1 ensures flexibility in ceramic selection and safe veneering
- ★ No cooling phase required, depending on the ceramics
- ★ Excellent metal-ceramic bonding, even without bonder
- ★ An oxidation firing can be omitted
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	508 MPa
Ultimate tensile strength	795 MPa
Elongation	9 %
Elastic modulus	209 GPa
Vickers hardness	300 HV 10
Density	8,3 g/cm ³
Melting range	1370 - 1435 °C
Preheating temperature	850 - 950 °C
Casting temperature	1535 - 1590 °C
CTE (25 - 600 °C)	14,1 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	5

QUANTITY	REF
1000 g	138000

★ DIASTAR

All-in-One diamonded polishing paste for metals, ceramics, zirconia, composites, plastics and acrylics.

- › Very high diamond content
- › Hard paste consistency, thereby more efficient dosing
- › No splashing or smearing - clean and economical
- › Not suitable for intraoral use!

VERSION	REF
1 Dose 30 g	271069



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	510 - 600 MPa
Ultimate tensile strength	770 - 780 MPa
Elongation	>3 %
Elastic modulus	200 - 230 GPa
Vickers hardness	355 HV 10
Density	8,4 g/cm ³
Melting range	1170 - 1390 °C
Preheating temperature	850 - 950 °C
Casting temperature	1490 - 1540 °C
Laser weldable	Yes
Typ (DIN EN ISO 22674)	5

QUANTITY	REF
1000 g	132100
250 g	132250



TECHNICAL PROPERTIES:	
Proof stress (Rp0.2)	500 MPa
Ultimate tensile strength	760 MPa
Elongation	6 %
Elastic modulus	250 GPa
Vickers hardness	380 HV 10
Density	8,1 g/cm ³
Melting range	1200 - 1385 °C
Preheating temperature	850 - 950 °C
Casting temperature	1485 - 1540 °C
CTE (25 - 600 °C)	14,9 x 10 ⁻⁶ K ⁻¹
Laser weldable	Yes
Typ (DIN EN ISO 22674)	5

QUANTITY	REF
1000 g	132000

★ MODELSTAR S

CoCr partial denture alloy for the whole range of removable partial dentures from combined fixed-removables restorations to clasp-retained dentures.

- › Free of nickel, beryllium, cadmium and lead
- › Type 5 according to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and corrosion-resistant
- › High wearing comfort due to low thermal conductivity

Composition (mass percentage):

Co: 62,7 % / Cr: 29 % / Mo: 6 % / C, Fe, Si, Mn: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ Excellent for casting of 3D printed plastic parts
- ★ System-free working due to very good alloy properties
- ★ Universally applicable for clasp-retained prostheses and combined techniques
- ★ Pleasant polishing properties and easy finishing
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking

★ STARBOND CO

CoCr partial denture alloy (bondable) for challenging combined restorations and gracile clasp design.

- › Free of nickel, beryllium, cadmium and lead
- › Type 5 according to DIN EN ISO 22674
- › High degree of purity
- › Biocompatible and corrosion-resistant
- › High wearing comfort due to low thermal conductivity
- › Spring-hard

Composition (mass percentage):

Co: 62 % / Cr: 30 % / Mo: 5,5 % / Si: 1 % / C, Fe, Mn: <1 %

ADVANTAGES FOR DENTAL TECHNICIANS:

- ★ Universally applicable for clasp-retained prostheses, combined techniques and ceramic restorations
- ★ Excellent for casting of 3D printed plastic parts
- ★ System-free working due to very good alloy properties
- ★ Pleasant polishing properties and easy finishing
- ★ Optimal conditions for laser welding
- ★ Application flexibility and easy melting, no sparking